



## Hoomline Brillant 55 Dryback

PROPERTIES	STANDARD	UNIT	TEST RESULT
Plank size	EN 427	cm	121,92 x 22,86 cm
Thickness	EN 428	mm	2,5 mm
Wearlayer	EN 429	mm	0,55 mm
Surface treatment			BP
Bevel			4-side bevel
Click			No
Weight per sqm	EN 430	gr/m2	3720
Pieces per box (plank)		piece	12
Sqm per box (plank)		m2	3,34
Boxes per pallet (plank)		box	68
Sqm per pallet (plank)		m2	227,43
Classification	EN 685	class	23
Fire classification	EN 13501-1	class	Bf1-S1
Slipresistance	DIN 51130	class	R10
	EN 13893	class	DS
Weargroup	EN 660-1		Type 1
Residual indentation	EN 433		0.05 mm
Thermal conductivity	EN 12667:2001		0.076 W/(m·K)
Thermal resistance	EN 12667:2001		0.036 m²·K/W
Electrostatic properties	EN 1815		<2.0 KV
Castor chair	EN 425		yes   type W   EN12529
Dimensional stability	EN 434		≤0.10%
Light fastness	ISO 105-BO2	degree	level ≥6 method A
Determination of impact sound	E 492-09		IIC=55
Sound reduction	ISO 717-2		6 dB
Chemical resistance	EN 423		yes
Floor heating system		degree	suitable   max.27°C
CE marking	EN 14041		EN 14041:2004+AC:2005+AC:2006
Guarantee			residential 25 years - commercial 10 years

Deutsches  
Institut  
für  
Bautechnik



CERTIFIED BY  
SCS Global Services

